

GreenPrime Metal



Description

- A high quality, water-based, rust inhibiting, low VOC primer.
- A self cross linking technology that provides low VOC levels with greater corrosion resistance and adhesion properties.
- Resists heat, cold, moisture and weathering.
- Dries quickly for a reduced time before elastomeric coating application.

Recommended Uses

GreenPrime Metal is used as a prime coat over metal surfaces but can also be applied to a wide range of substrates including wood, metal, concrete, masonry, various single ply membranes, spray polyurethane foam and most commonly used roof coatings. Low VOC levels allow application in most air quality restrictive areas. Fast drying and increases in roof surface temperature are provided by the dark red color.

Colors

Dark Red

Packaging/Shipping Information

CONTAINER SIZE

Part A: 5 Gallon pail with 4 Gallons

Part B: 1 Gallon pail

SHIPPING CLASS

Class 55

Class 55

Property	Result
Total Solids	41% ± 3%
Weight per Gallon	10.0 lbs per gallon ± 0.2
VOC	65 g/liter
Clean Up	Water
Shelf Life-unopened	12 months @ 40-90°F
Viscosity	800 ±200 cP

Meets Requirements for ASTM D6083 Acrylic Elastomeric Roof Coating



Energy Efficient Building Product Solutions

4008 Louetta Road, Suite #464 • Spring, TX 77388
877.GRN.SHLD • www.greenshieldproducts.com



GreenPrime Metal



SURFACE PREPARATION

Surface must be clean, dry and free of loose particles or other foreign matter. Pressure washing is required on metal surfaces showing signs of oxidation.

APPLICATION

This product may be brushed rolled or sprayed on a clean, dry surface. For details see Equipment Recommendations at the end of this sheet. If sprayed, material should be at least 75° C. Before applying additional coat, the previous coat must be completely dry and cured. If any contamination is present on the cured surface it must be washed and completely dry before application of subsequent coats.

Application properties

Yield (1 gal 200 to 400 sq ft)	
Dry Time (75° F)	2 to 3 hours
Recoat window	2 to 3 hours
Complete Cure	

COVERAGE RATE:

Apply GreenPrime Metal at the rate of 1 gallon per 200 sq. ft. (48 wet mils). Surface texture and wind will affect applied mil thickness.

ENVIRONMENTAL CONDITIONS

This product cures by water evaporation only. Product must not be applied when the ambient temperature is below 50°F or if there is any possibility it could fall below 32°F within 24 hours of application. Application is not recommended if rain or dew is likely to occur before product dries. In high humidity conditions late afternoon applications should be avoided as overnight dew formation on uncured surface can cause coating wash-off. On marginal days, multiple applications of thin coats can ensure proper drying before rain or overnight freezes

PONDED WATER

- GreenShield warranties do not cover damage due to ponding water.
- The National Roofing Contractors Association considers ponding water on any roof unacceptable. (See the NRCA Roofing and Waterproofing Manual).

LIMITATIONS

Surface must be clean and dry. Application is not recommend on roofs with slopes less than 1/8 in 12 or where ponded water is present. Do not apply over wet substrates or when inclement weather is imminent. Complete cure of GreenPrime Metal requires complete evaporation of water. Cool temperatures and high humidity retard cure. Do not leave product exposed to elements for more than 48 hours to prevent weathering and dirt pick up that will compromise adhesive performance properties.

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. Information sources include but are not limited to MSDS and product labels. More resources are available at polyurethane.org, sprayfoam.org, or by contacting GreenShield Products directly.

EQUIPMENT

- Minimum requirements:

Roller

- 1 1/4" nap roller

Spray

- 30:1 fluid to air ratio capable pump
- 2 1/2 gallons or more per minute (continuous)
- Filter screen 30 mesh or larger
- Hose rated to 2x maximum pump pressure
- Hose lining should be compatible with coating and required cleanout materials
- Hose lengths : (Largest diameter at pump)
 - 3/8 minimum 6 ft wip
 - 3/8 minimum I.D. up to 75 feet
 - 1/2 minimum I.D. up to 200 feet
 - 3/4 minimum I.D. over 200 feet
- Spray gun: Graco Hydra Mastic or equivalent
- Spray Tip:
 - Reversible self-cleaning type
 - Orifice size of .027 to .039
 - Fan angle of 40° to 50°
- Always use components rated for pump pressures.



Energy Efficient Building Product Solutions

4008 Louetta Road, Suite #464 • Spring, TX 77388
877.GRN.SHLD • www.greenshieldproducts.com

